

Closed Mesh Polypropylene

Colors: Green, Black

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	420	225
Trapezoid Tear Strength	ASTM D 4533	lbs	125	90
Shade		%	95	
Air Flow	ASTM D 737	cfm	>150	

Physical Properties	Test Method	Unit	Typical Roll Value
Weight	ASTM D 5261	oz/yd sq.	4.9
Construction		EPI/PPI	30 x 16
Fiber Content			100% PP

Thermal Properties	
Softening & Melting Temperature	Soften at 300-310 degrees Fahrenheit and melt at 325-335 degrees Fahrenheit.
Shrinkage	Shrinkage at boil, 3-9% Shrinkage at 250 degrees Fahrenheit, 5-12.5%
Flammability	Difficult to ignite and upon burning it melts to a bead. Proper additives can produce flame retardancy.

Additional Properties	
Effects of Moisture	Polypropylene does not absorb moisture.
Abrasion Resistance	Polypropylene has excellent abrasion resistance.
Mildew & Insect Resistance	Insects and mildew do not attach to polypropylene.
Identification	Melting point: 325 to 335 degrees Fahrenheit.
Tensile Properties	Polypropylene monofilaments have an average tenacity range of 4-7 grams per denier. Polypropylene has an ultimate elongation of 14-30%

Disclaimer: Zaino Tennis Courts assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Zaino Tennis Courts disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.